

Marquette University

e-Publications@Marquette

---

School of Dentistry Faculty Research and  
Publications

Dentistry, School of

---

8-2016

## Dental Applications of Natural-Origin Polymers in Hard and Soft Tissue Engineering

Hossein E. Jazayeri  
*Marquette University*

Mina D. Fahmy  
*Marquette University*

Mehdi Razavi  
*Brunel University*

Brett E. Stein  
*University of Pennsylvania*

Aatif Nowman  
*Marquette University*

*See next page for additional authors*

Follow this and additional works at: [https://epublications.marquette.edu/dentistry\\_fac](https://epublications.marquette.edu/dentistry_fac)



Part of the [Dentistry Commons](#)

---

### Recommended Citation

Jazayeri, Hossein E.; Fahmy, Mina D.; Razavi, Mehdi; Stein, Brett E.; Nowman, Aatif; Masri, Radi; and Tayebi, Lobat, "Dental Applications of Natural-Origin Polymers in Hard and Soft Tissue Engineering" (2016). *School of Dentistry Faculty Research and Publications*. 189.

[https://epublications.marquette.edu/dentistry\\_fac/189](https://epublications.marquette.edu/dentistry_fac/189)

---

**Authors**

Hossein E. Jazayeri, Mina D. Fahmy, Mehdi Razavi, Brett E. Stein, Aatif Nowman, Radi Masri, and Lobat Tayebi

# Dental Applications of Natural-Origin Polymers in Hard and Soft Tissue Engineering

**Hossein E. Jazayeri**

*University of Pennsylvania School of Dental Medicine,  
Philadelphia, PA.*

*School of Dentistry, Marquette University,  
Milwaukee, WI*

**Mina D. Fahmy**

*School of Dentistry, Marquette University,  
Milwaukee, WI*

**Mehdi Razavi**

*BCAST, Institute of Materials and Manufacturing,  
Brunel University London,  
Brunel Institute for Bioengineering, Brunel University London,  
Uxbridge, London, UK*

**Brett E. Stein**

*University of Pennsylvania School of Dental Medicine,  
Philadelphia, PA*

**Aatif Nowman**

*School of Dentistry, Marquette University,  
Milwaukee, WI*

**Radi M. Masri**

*Department of Endodontics, Prosthodontics and Operative  
Dentistry, University of Maryland School of Dentistry,  
Baltimore, MD*

**Lobat Tayebi**

*School of Dentistry, Marquette University,  
Milwaukee, WI*

*Department of Engineering Science, University of Oxford,  
Oxford, UK*

**Abstract:** Clinical advances in the treatment of dentoalveolar defects continue to evolve with the introduction of new innovations in regenerative medicine and tissue bioengineering. Recent developments in tissue engineering are aimed at safely and effectively regenerating a damaged or necrotic area by replenishing its cells and increasing surrounding gene expression. Various techniques have successfully given rise to porous scaffolds being used by clinicians to treat the defect and initiate the repair process. Tissue reconstruction using bioengineered scaffolds is advantageous over traditional autografting, since it prevents the instigation of pain and donor site morbidity while ultimately creating both the environment and machinery needed to induce cell proliferation, migration, and reattachment within the affected area. This review article aims to describe and review the available literature regarding the regenerative capacity of natural polymers used for the treatment of dentoalveolar defects. The repair mechanisms, advantages of protein and polysaccharide derivatives, and the potential of stem cell therapy are discussed.

Bone resorption is a progressive process that complicates restoration of edentulous and partially edentulous areas.<sup>1,2</sup> Bone loss compromises the periodontal health of teeth, complicates placement of dental implants<sup>3</sup> and in advanced cases may cause remarkable changes in facial morphology.<sup>4</sup>

Tissue regeneration in the form of grafting using bone substitutes is used extensively for patient treatment. Every year in the United States, approximately 500,000 bone grafting procedures are performed in dental and medical offices. The market for bone substitutes used in these procedures is valued near 1 billion dollars.<sup>5</sup>

In 2012, the market for biomaterials used exclusively in dental procedures was valued at 222 million dollars, and this number continues to grow.<sup>6</sup>

With the advent of tissue engineering, specific materials and scaffolds have been produced to effectively deliver synthetic and biological agents capable of tissue regeneration.<sup>7-17</sup> Scaffolds must effectively facilitate the early stages of regeneration before transitioning to a natural mode of self-repair.<sup>18-26</sup> In addition to delivering regenerative biomaterials, scaffolds seal off the affected area and protect it from infection, restore the extracellular matrix (ECM), and induce proliferation and differentiation of cells composing the four primary types of dental tissue: bone, cementum, connective tissue, and gingival epithelium.<sup>27,28</sup> Therefore, scaffolds can be used in various dental applications and preprosthetic surgery including guided tissue regeneration and treatment of periodontal disease,<sup>29</sup> osteogenic repair of the alveolar process and bone augmentation procedures to increase volume of bone and restore bony defects prior to endosseous implant surgery, craniofacial bone defect repair,<sup>30</sup> socket preservation procedures, and in the treatment of ailing/failing dental implants.<sup>31</sup>

In the last decade, the use of bioprinted scaffolds composed of natural polymers and stem cells has remarkably allowed for repair of an array of defects while mimicking the human ECM.<sup>32</sup> The ECM contains molecules that contribute to the strength and flexibility of the periodontium.<sup>33</sup> The presence of growth factors in the matrix is important in the process of regeneration, and the combination of abundant biomolecules and signaling mechanisms within the ECM assists in the differentiation of progenitor cell populations, replenishing the mature cells native to a healthy bone and gingival tissue.<sup>34,35</sup> Strong adhesion of cells to ECM proteins holds functional necessity, is vital to tissue integrity, and is a significant goal in restoring the chemical nature of the environment to be restored and augmented.<sup>36</sup>

The focus of this manuscript is to review materials used in 3D bioprinting of scaffolds, including polysaccharide derivatives, protein derivatives, and stem cells, that can restore the necessary interaction between the cells and matrix in preprosthetic surgery requiring tissue engineering. Nearly 100 papers in journals from both the United States and abroad dating from 1972 until 2015 were used to compile

information regarding the application of each polymer in the regeneration of dentoalveolar and maxillofacial tissues. Papers focusing on biomaterial characteristics and the clinical effects of tissue engineering were analyzed alike and cited to write the manuscript on this multidisciplinary topic.

## **Polysaccharide derivatives**

### *Chitosan*

Chitosan is a biopolymer obtained from chitin, a nitrogen-containing polysaccharide derived from glucose. Chitosan is biocompatible, flexible, and antibacterial and can accelerate wound healing.<sup>37</sup> It can be shaped into various structures, including microspheres,<sup>38</sup> paste,<sup>39</sup> sponges,<sup>40</sup> and porous scaffolds,<sup>41</sup> and therefore, it has the potential to be used in tissue engineering.<sup>42</sup> Lahiji et al<sup>43</sup> noted that chitosan can be successfully used as a template for bone defect restorations, due to its ability to support viable osteoblasts. A study on the effects of chitosan on socket preservation after extraction showed that the bone densities in the middle and apical sections of the repaired socket were significantly greater in chitosan-treated sockets than the untreated, unfilled control group, concluding that it can be used for bone repair in the cases of bone loss.<sup>44</sup> In another study, chitosan was used to restore bony defects in the upper tibia of rats. The results showed that compared to the control, in which chitosan powder was not used to fill the defect, bone repair was significantly expedited in the chitosan group at 1 week and 4 weeks post-surgery.<sup>45</sup> Further attesting to chitosan potential in tissue engineering, Muzzarelli et al<sup>46</sup> demonstrated that chitosan ascorbates produced in the gel form are fit for the regeneration of periodontal ligament (PDL) tissues. They also demonstrated that the chitosan was gradually reabsorbed in hosts with a satisfactory clinical recovery of periodontal defects, where both tooth mobility and pocket depths were significantly reduced.

Because of its biocompatibility and bioactivity, chitosan can be combined with several inorganic materials to make 3D microstructures to be used as scaffolds. Examples of these inorganic materials include bioactive glass, hydroxyapatite, alginate, collagen, and recombinant

vectors. Bioactive glass, as the name implies, has excellent bioactivity and when added to chitosan membranes would promote guided bone regeneration.<sup>37</sup> Mota et al<sup>37</sup> showed that membranes containing chitosan/bioactive glass nanoparticles, in contrast to pure chitosan membranes, were able to stimulate the deposition of an apatite layer, which highlights the advantages of a composite scaffold.

Another inorganic material that can be combined with chitosan is hydroxyapatite, which is known for its biocompatibility and its osteoconductive potential.<sup>47,48</sup> Kong et al<sup>49</sup> developed a homogenous nanohydroxyapatite/chitosan porous scaffold that possessed better biocompatibility than a pure chitosan scaffold, while also allowing a higher proliferation of cells. In agreement with Kong et al's findings, Zhang et al<sup>50</sup> concluded that a nanohydroxyapatite/chitosan scaffold had better cytocompatibility than a pure chitosan scaffold.

Other materials have been used to enhance the strength of chitosan-based scaffolds. Li et al<sup>51</sup> used alginate to construct a chitosan/alginate composite with significantly enhanced mechanical strength. The chitosan/alginate scaffold allowed seeded osteoblasts to attach and proliferate well in culture without the use of an osteogenic medium and promoted quicker deposition of minerals compared to pure chitosan.

Zhang et al<sup>52</sup> used chitosan/collagen scaffolds to create a porous structure that could be loaded with plasmids and adenoviral vectors encoding human transforming growth factor- $\beta$ 1 (TGF- $\beta$ 1). Human PDL cells were seeded within the scaffold's pores and implanted into athymic mice. It was found that no inflammatory reaction or extrusions occurred, confirming the biocompatibility of this TGF- $\beta$ 1 encoding scaffold. This scaffold also showed the highest proliferation rate as well as upregulated expression of both type I and type III collagen. Moreover, tagged human PDL cells caused surrounding tissues to grow within the porous scaffolds. The study concluded that the chitosan/collagen composite scaffold encoding TGF- $\beta$ 1 is a candidate that could work well for periodontal tissue regeneration.

## Cellulose

Cellulose membranes were the first biomaterial employed as surgical barriers for guided tissue regeneration, followed by expanded polytetrafluoroethylene (ePTFE) and some other biodegradable polymers.<sup>53-55</sup> Cellulose and ePTFE have been introduced with the commercial names of Millipore filter and Gore-Tex as non-resorbable biomaterials for cell-occlusive barriers used for tissue regeneration.<sup>55</sup>

As a relevant form of cellulose in tissue engineering, microbial cellulose (MC) is a polysaccharide that has been developed from *Acetobacterxylinum*.<sup>56</sup> In addition to its use in the treatment of periodontal defects, guided-tissue regeneration, and preprosthetic surgery, MC membranes offer many other applications in regenerative medicine, including their use as a graft for dura mater surrounding brain tissues.<sup>56</sup> MC has been previously used in wound-healing, confirming its promise as a product in the biomaterials field.<sup>56</sup> MC membranes have been employed as a scaffold material to increase cell attachment.<sup>57</sup> Wan et al<sup>58</sup> synthesized a MC membrane coated with hydroxyapatite and found that mesenchymal stem cells (MSC) attached and proliferated onto the MC membrane with a low inflammatory response.<sup>58</sup>

In vivo studies using MC demonstrated that MC samples did not cause any macroscopic inflammatory responses after 1 and 3 weeks of implantation,<sup>56</sup> confirming findings from in vitro experiments.<sup>58</sup> MC has also been used as a physical barrier in periodontal regeneration, to separate incised oral epithelial cells and gingival connective tissue from the treated root surface, allowing PDL cells to proliferate inside the treated area, leading to tissue regeneration.<sup>56,59</sup>

Another form of cellulose used in tissue engineering is cellulose hydrogels. They have been shown to be biocompatible with connective tissues. In vitro experiments on cellulose hydrogels revealed that this material has potential to enhance osteoblast cell attachments and proliferation for bone tissue engineering.<sup>60</sup>

## Protein derivatives

### *Collagen*

Collagen, an extremely abundant protein and defining component of connective tissue throughout the body, is a potent biomaterial with a vast potential for tissue regeneration. Examples of collagen's beneficial role during tissue repair include surrounding tissue compatibility, biodegradability, induction of epithelial regeneration,<sup>61</sup> and its low immunogenicity and cytotoxicity.<sup>62</sup> More specifically, due to its low immunogenicity, collagen fosters the growth of a native ECM, is chemotactic for fibroblasts, and induces a cascade by which the internal matrix is further developed.<sup>63</sup>

Collagen has a strong osteoinductive effect, stimulating osteoblast differentiation and proliferation, which would lead to bone growth. Collagen also increases gene expression for morphogenic proteins, such as BMP.<sup>44</sup> To engineer skeletal tissues, a scaffold should contain a significant number of progenitor cells in addition to bioactive agents that can draw in cells with a restorative functionality to the site of damage.<sup>64,65</sup> Collagen plays a crucial role in facilitating this biological process because it acts as an anchor for the attachment of proteoglycans and glycosaminoglycans, improving the overall mechanical strength and stability of the regenerated tissue.<sup>66</sup> While collagen's inductive role in BMP expression has demonstrated a strong, notable regeneration of the peri-implant and periodontal defects, previous *in vivo* studies demonstrate that duration of BMP availability and activity in scaffolds is limited.<sup>67</sup>

The rehabilitative potential of collagen in tissue engineering lies primarily in its use for delivering plasmids and adenoviral vectors. For example, a study examining the combination of adenovirus encoding PDGF-B (AdPDGF-B) with a collagen gel noted an increase in the area of cementum, filling of alveolar defects, and an increase in bone volume.<sup>68</sup> However, the target tissue and type of collagen in the scaffold are important factors to consider because different types of collagen may provide different degrees of biocompatibility, immunogenicity, degradation rates, and different mechanical properties of the scaffold.<sup>69,70</sup> For example, types I and III collagen are

known to make up the PDL,<sup>71</sup> and type IV collagen makes up the basement membrane of junctional epithelium and the epithelial rests of the PDL.<sup>72</sup>

## *Fibrin*

As a natural protein, fibrin is synthesized from fibrinogen, which may be autologously harvested from the human body.<sup>73</sup> Polymerized fibrin is a main constituent of blood clots and has an important function in the later wound-healing processes.<sup>74</sup> Due to its natural ability to enhance cellular interaction and follow scaffold remodeling compared to the synthetic scaffolds, fibrin has found a well-established application in various areas of research in regenerative dentistry.<sup>75</sup> Fibrin provides a biocompatible carrier for biomolecules and presents a substrate for adhesion of tissue-forming cells such as endothelial cells, and fibroblasts, which are engaged in angiogenesis and are responsible for remodeling of the new regenerated tissues.<sup>76</sup>

Fibrin provides suitable locations for cell-substrate binding, and therefore it mimics the native tissue<sup>77</sup> and allows for remodeling by cell-associated proteolytic activity.<sup>78</sup> Fibrin gel has been produced recently with a shape of three-layered human PDL cell sheets and transplanted with a human dentin block subcutaneously into the back of a rat. The results of histological evaluations revealed that the human PDL cells/dentin blocks stimulated a new cementum-like hard tissue on the surfaces of more than 60% of the samples after 6 weeks of implantation.<sup>79</sup>

Fibrin glue has also been used with periosteal cell/matrix hybrids to form new bone at heterotopic sites in nude mice. The periosteal cells were mixed with fibrin glue in a syringe, and then the cell/matrix-fibrin glue was injected on the dorsum of athymic nude mice. After 3 months, histological evaluations confirmed the ability of fibrin glue carrier to cause new bone formation.<sup>80</sup>

Fibrin enhances the mitogenic response of the periosteum during the bone-healing process by trapping and activating platelets that cause the secretion of growth factors, such as platelet-derived growth factor, transforming growth factor, and insulin-like growth factor I.<sup>81,82</sup> Choukroun et al<sup>83</sup> developed a fibrin matrix known as a

platelet-rich fibrin (PRF) in order to hold platelet cytokines and cells before releasing them after a predetermined time. Gassling et al<sup>76</sup> showed that PRF is an excellent scaffold material for proliferation of human periosteal cells, with a great potential for use in tissue engineering; however, the imperative property of PRF is a profit not only due to its biocompatibility, but also because of its lower costs.<sup>76</sup>

Numerous researchers have confirmed fibrin as an appropriate scaffold for adherence, colonization, and proliferation of human mesenchymal stem cells (HMSC).<sup>84,85</sup> Therefore, using fibrin as an autologous scaffold for periosteal cell or stem cell transplantation and for bone tissue engineering is a promising application; however, its fast biodegradability may be a disadvantage for its use as a shape-specific scaffold in tissue engineering. Thus, optimizing fibrin composition is an area requiring further research to acquire a scaffold system that provides the best shape integrity.<sup>75</sup>

## *Stem cells*

Preclinical investigations revealed that stem cell delivery can be used to create consistent and efficient outcomes in managing dental and orofacial defects,<sup>86,87</sup> so that some clinical trials employing in vitro expanded stem cells have begun or are in progress. The first clinical alveolar bone reconstruction was conducted in 2009 using dental pulp stem cells (DPSCs). This work proposed that a dental pulp stem cells/collagen sponge biocomplex can entirely repair human mandible defects and demonstrated that this cell population could be employed for the regeneration of organs. In 2011, there was an approved clinical study for periodontal regenerative therapy using cell sheet technology. The results of this work indicated that the use of autologous PDL cell sheets and  $\beta$ -tricalcium phosphate ( $\beta$ -TCP) could restore the defects of alveolar bone and PDL tissue.<sup>86,87</sup>

Due to the lack of native stem cells, tissue regeneration does not naturally occur in bone defects. For this reason, exogenous regenerative materials including in vitro manipulated stem cells are required to encourage the host cell niche and help tissue repair.<sup>88</sup> Stem cells and/or progenitor cells are typically cultured ex vivo and used to treat patients as biological agents.<sup>89</sup> A promising source of stem cells needs to have high proliferation ability, ability to

differentiate into intended types of cells, low antigenicity, and easy manipulation into expanded processing. PDL stem cells (PDLSCs), stem cells from apical papilla (SCAP), stem cells from human exfoliated deciduous teeth (SHED), and bone marrow mesenchymal stem cells (BMSCs) are the common potential cell sources being employed in dental tissue engineering.<sup>87,89</sup> These cells are isolated from the dental tissue, bone marrow, and adipose, and then they are proliferated and implanted into the periodontal defect using either biomaterial-free or biomaterial-based scaffolds.<sup>90</sup> Otherwise, the cells may be allogeneic from a cell bank.<sup>87</sup> Recent reports have shown that MSC have been used for the regeneration of PDL, cementum, and alveolar bone in vivo.<sup>90,91</sup>

BMSCs can be used practically in periodontal tissue engineering.<sup>91-93</sup> In one study, biodegradable collagen as the biomaterial scaffold supported BMSCs during implantation.<sup>94</sup> The results of another study on the implantation of cultured human PDL stem cells into the produced periodontal defects in rats demonstrated that the stem cells were adhered to both the alveolar bone and cementum surfaces, and there was an indication of the development of a PDL-like structure.<sup>95,96</sup> Stem cell therapy will need to consider the costs, provide help to patients, satisfy regulatory agencies, meet enhanced stem cell supplies, be covered by medical insurance, and prove lucrative for pharmaceutical companies to get to the final stages of clinical applications.<sup>87</sup>

## Summary

The applications of natural polymers have proven to be extremely potent in preprosthetic surgery and in periodontal tissue regeneration. In every substance, the biocompatibility and induction of cell migration and attachment are essential for a successful repair. Although minor differences exist between the polysaccharide and protein derivatives, the overall goal is that scaffold implantation and cellular activity guides regeneration of all components of the periodontium. These biological agents target the soft tissue and underlying hard tissue, and the addition of a growth factor can further stimulate vascularization and osteoprogenitor differentiation, for example, to repair the resorbed bone. The mimicry of a native matrix

allows for normal biochemical processes. A leading candidate for alternative treatment, stem cell therapy, was also examined. In vitro testing has shown that stem cells hold great promise for the future of regenerative dentistry. All the natural origin polymers covered in this mini review (Table 1) are the most widely recognized treatment agents, and we have demonstrated comprehensively, with the support of material characteristics and clinical applications (Table 2), that the potential for each can induce repair of periodontal and craniofacial defects.

**Table 1.** Summarized material characteristics

	<b>Chitosan</b>	<b>Cellulose</b>	<b>Collagen</b>	<b>Fibrin</b>
Advantages	-Biocompatible -Antibacterial -Wound healing	-Enhanced cell attachment -No macroscopic inflammatory effect	-Low immunogenicity -Strong osteoconductivity	-Mimics native tissue  -Enhances mitogenic response of periosteum
Disadvantages	-Poor mechanical strength	-Cytotoxic effects	-Poor mechanical properties	-Rapid biodegradability
Suggested materials to form the potent composite	-Bioactive glass -Hydroxyapatite -Alginate -Collagen	-Hydroxyapatite -Chitosan -Pectin	-Hydrogel -PLGA -Hyaluronic Acid -Hydroxyapatite -Bioglass	-Collagen -Polyurethane -Hydroxyapatite -Calcium Phosphate -Polylactide

**Table 2.** Summarized clinical applications

	<b>Chitosan</b>	<b>Cellulose</b>	<b>Collagen</b>	<b>Fibrin</b>
Clinical mode of delivery	-Nanofiber membrane for GTR -Sponge -Electrospun nanofibers -Bioactive coating	-Surgical barrier placement for GTR -Injectable gels -3D scaffold	-Porous sponge implantation -3D scaffold -Injectable gels	-Fibrin gel -Fibrin glue -Fibrin microbeads -3D scaffold
On-site advantages	-One of the most potent curative materials used -Enhanced proliferation of human PDL cells -Enhanced angiogenesis	-Has a unique nanofibrillar composition that mimics a perfect matrix for regeneration -Allows for rapid healing -Serves as a barrier against infection	-Extremely biocompatible -Controls preodontoblast rearrangement and their adhesion to pulp tissue -Widely used in maxillofacial and	-Instigates hemostasis and tissue bonding -Minimizes blood loss -Combats bacterial infection at the site of injury -Successful use of fibrin-based

	<b>Chitosan</b>	<b>Cellulose</b>	<b>Collagen</b>	<b>Fibrin</b>
			alveolar bone grafting	scaffold in regenerative endodontics observed as well as regeneration of peri-implant defects, socket preservation, and healing of sinus perforations
Complications	-Uncontrolled dissolution in some cases  -Low durability under compression of maxillofacial bone	-Inflammatory reaction noted in several in vivo studies for bone engineering	-Lack of durability under compression of maxillofacial bone -Loses capacity to maintain space in humid environment -Animal allograft of collagen could transmit disease	-Rapid shrinkage remains a serious concern for clinicians -Requires use as a composite scaffold to overcome low mechanical strength
Study type	-In vitro -In vivo -Clinical trial	-In vitro -In vivo -Clinical trial	-In vitro -In vivo -Clinical trial	-In vitro -In vivo -Clinical trial

## **Acknowledgment**

The authors are thankful for the useful discussions with Pinkesh Shah and Matthew Bures and the support from Marquette University Strategic Innovation Fund.

## **References**

- <sup>1</sup>Tallgren A: The continuing reduction of the residual alveolar ridges in complete denture wearers: a mixed-longitudinal study covering 25 years. *J Prosthet Dent* 1972;27:120-132
- <sup>2</sup>Lang NP, Pun L, Lau KY, et al: A systematic review on survival and success rates of implants placed immediately into fresh extraction sockets after at least 1 year. *Clin Oral Implants Res* 2012;23(Suppl 5):39-66
- <sup>3</sup>Ten Heggeler JM, Slot DE, Van der Weijden GA: Effect of socket preservation therapies following tooth extraction in non-molar regions in humans: a systematic review. *Clin Oral Implants Res* 2011;22:779-788
- <sup>4</sup>Tallgren A: The continuing reduction of the residual alveolar ridges in complete denture wearers: a mixed-longitudinal study covering 25 years. 1972. *J Prosthet Dent* 2003;89:427-435

- <sup>5</sup>Greenwald AS, Boden SD, Barrack RL, et al: The evolving role of bone-graft substitutes. *American Academy of Orthopaedic Surgeons, 77th Annual Meeting. New Orleans, Louisiana, 2010.* Available online <http://www.aatb.org/aatb/files/ccLibraryFiles/Filename/000000000322/BoneGraftSubstitutes2010.pdf>. Accessed December 17, 2015
- <sup>6</sup>U.S. dental bone graft substitutes and other biomaterials market. [http://www.slideshare.net/Reports\\_Corner/us-dental-bone-graft-substitutes-and-other-biomaterials-market-reports-corner](http://www.slideshare.net/Reports_Corner/us-dental-bone-graft-substitutes-and-other-biomaterials-market-reports-corner). Reports Corner, 2013. Accessed October 26, 2015
- <sup>7</sup>Yazdimamaghani M, Razavi M, Vashae D, et al: Development and degradation behavior of magnesium scaffolds coated with polycaprolactone for bone tissue engineering. *Mater Lett* 2014;132:106-110
- <sup>8</sup>Razavi M, Fathi M, Savabi O, et al: In vitro study of nanostructured diopside coating on Mg alloy orthopedic implants. *Mater Sci Eng C Mater Biol Appl* 2014;41: 168-177
- <sup>9</sup>Mozafari M, Vashae D, Tayebi L, et al: *Electroconductive Nanocomposite Scaffolds: A New Strategy into Tissue Engineering and Regenerative Medicine*. Croatia, European Union: INTECH Open Access Publisher, 2012
- <sup>10</sup>Razavi M, Fathi M, Savabi O, et al: Microarc oxidation and electrophoretic deposition of nano-grain merwinite (Ca<sub>3</sub>MgSi<sub>2</sub>O<sub>8</sub>) surface coating on magnesium alloy as biodegradable metallic implant. *Surf Interface Anal* 2014;46:387-392
- <sup>11</sup>Shabafrooz V, Mozafari M, Köhler GA, et al: The effect of hyaluronic acid on biofunctionality of gelatin–collagen intestine tissue engineering scaffolds. *J Biomed Mater Res A* 2014;102:3130-3139
- <sup>12</sup>Salahinejad E, Hadianfard M, Macdonald D, et al: Aqueous sol–gel synthesis of zirconium titanate (ZrTiO<sub>4</sub>) nanoparticles using chloride precursors. *Ceramics Int* 2012;38:6145-6149
- <sup>13</sup>Salahinejad E, Hadianfard M, Macdonald D, et al.: Multilayer zirconium titanate thin films prepared by a sol–gel deposition method. *Ceramics Int* 2013;39:1271-1276
- <sup>14</sup>Rouhani P, Salahinejad E, Kaul R, et al: Nanostructured zirconium titanate fibers prepared by particulate sol–gel and cellulose templating techniques. *J Alloys Compounds* 2013;568:102-105
- <sup>15</sup>Salahinejad E, Hadianfard MJ, Macdonald DD, et al: In vitro electrochemical corrosion and cell viability studies on nickel-free stainless steel orthopedic implants. *PLoS One* 2013;8:e61633
- <sup>16</sup>Razavi M, Fathi MH, Savabi O, et al: Biodegradation, bioactivity and in vivo biocompatibility analysis of plasma electrolytic oxidized (PEO) biodegradable Mg implants. *Phys Sci Int J* 2014;4:708-722

- <sup>17</sup>Yazdanpanah A, Kamalian R, Moztarzadeh F, et al: Enhancement of fracture toughness in bioactive glass-based nanocomposites with nanocrystalline forsterite as advanced biomaterials for bone tissue engineering applications. *Ceram Int* 2012;38:5007-5014
- <sup>18</sup>Yazdimamaghani M, Razavi M, Vashae D, et al: Microstructural and mechanical study of PCL coated Mg scaffolds. *Surf Eng* 2014;30:920-926
- <sup>19</sup>Tahmasbi Rad A, Ali N, Kotturi HSR, et al: Conducting scaffolds for liver tissue engineering. *J Biomed Mater Res A* 2014;102:4169-4181
- <sup>20</sup>Yazdimamaghani M, Vashae D, Assefa S, et al: Green synthesis of a new gelatin-based antimicrobial scaffold for tissue engineering. *Mater Sci Eng C* 2014;39:235-244
- <sup>21</sup>Yazdimamaghani M, Razavi M, Vashae D, et al: Surface modification of biodegradable porous Mg bone scaffold using polycaprolactone/bioactive glass composite. *Mater Sci Eng C* 2015;49:436-444
- <sup>22</sup>Yazdimamaghani M, Razavi M, Vashae D, et al: Significant degradability enhancement in multilayer coating of polycaprolactone-bioactive glass/gelatin-bioactive glass on magnesium scaffold for tissue engineering applications. *Appl Surf Sci* 2015;338:137-145
- <sup>23</sup>Heidari F, Bahrololoom ME, Vashae D, et al: In situ preparation of iron oxide nanoparticles in natural hydroxyapatite/chitosan matrix for bone tissue engineering application. *Ceram Int* 2015;41:3094-3100
- <sup>24</sup>Yazdimamaghani M, Vashae D, Assefa S, et al: Hybrid macroporous gelatin/bioactive-glass/nanosilver scaffolds with controlled degradation behavior and antimicrobial activity for bone tissue engineering. *J Biomed Nanotechnol* 2014;10:911-931
- <sup>25</sup>Shahini A, Yazdimamaghani M, Walker KJ, et al: 3D conductive nanocomposite scaffold for bone tissue engineering. *Int J Nanomed* 2014;9:167-181
- <sup>26</sup>Shabafrooz V, Mozafari M, Vashae D, et al: Electrospun nanofibers: from filtration membranes to highly specialized tissue engineering scaffolds. *J Nanosci Nanotechnol* 2014;14:522-534
- <sup>27</sup>Bartold PM, McCulloch CA, Narayanan AS, et al: Tissue engineering: a new paradigm for periodontal regeneration based on molecular and cell biology. *Periodontol 2000* 2000;24:253-269
- <sup>28</sup>Mozafari M, Salahinejad E, Shabafrooz V, et al: Multilayer bioactive glass/zirconium titanate thin films in bone tissue engineering and regenerative dentistry. *Int J Nanomed* 2013;8:1665-1672
- <sup>29</sup>Rios HF, Bashutski JD, McAllister BS, et al: Emerging regenerative approaches for periodontal reconstruction: practical applications from the AAP Regeneration Workshop. *Clinic Adv Periodontics* 2015;5:40-46

- <sup>30</sup>Fisher BA, Kohli N, Das A, et al: Current concepts of bone tissue engineering for craniofacial bone defect repair. *Craniomaxillofac Trauma Reconstr* 2015;8:23-30
- <sup>31</sup>Vignoletti F, Nunez J, Sanz M: Soft tissue wound healing at teeth, dental implants and the edentulous ridge when using barrier membranes, growth and differentiation factors and soft tissue substitutes. *J Clin Periodontol* 2014;41(Suppl 15):S23-S35
- <sup>32</sup>Murphy SV, Atala A: 3D bioprinting of tissues and organs. *Nature Biotechnol* 2014;32:773-785
- <sup>33</sup>Uitto VJ, Larjava H: Extracellular matrix molecules and their receptors: an overview with special emphasis on periodontal tissues. *Crit Rev Oral Biol Med* 1991;2:323-354
- <sup>34</sup>Dangaria SJ, Ito Y, Walker C, et al: Extracellular matrix-mediated differentiation of periodontal progenitor cells. *Differentiation* 2009;78:79-90
- <sup>35</sup>Terranova VP, Wikesjo UM: Extracellular matrices and polypeptide growth factors as mediators of functions of cells of the periodontium. A review. *J Periodontol* 1987;58:371-380
- <sup>36</sup>Cochran DL, Wozney JM: Biological mediators for periodontal regeneration. *Periodontol 2000* 1999;19:40-58.
- <sup>37</sup>Mota J, Yu N, Caridade SG, et al: Chitosan/bioactive glass nanoparticle composite membranes for periodontal regeneration. *Acta Biomater* 2012;8:4173-4180
- <sup>38</sup>Jameela S, Misra A, Jayakrishnan A: Cross-linked chitosan microspheres as carriers for prolonged delivery of macromolecular drugs. *J Biomater Sci Polym Ed* 1995;6:621-632
- <sup>39</sup>Maruyama M, Ito M: In vitro properties of a chitosan-bonded self-hardening paste with hydroxyapatite granules. *J Biomed Mater Res* 1996;32:527-532
- <sup>40</sup>Seol Y-J, Lee J-Y, Park Y-J, et al: Chitosan sponges as tissue engineering scaffolds for bone formation. *Biotechnol Lett* 2004;26:1037-1041
- <sup>41</sup>Costa-Pinto AR, Salgado AJ, Correlo VM, et al: Adhesion, proliferation, and osteogenic differentiation of a mouse mesenchymal stem cell line (BMC9) seeded on novel melt-based chitosan/polyester 3D porous scaffolds. *Tissue Eng Part A* 2008;14:1049-1057
- <sup>42</sup>Spin-Neto R, De Freitas RM, Pavone C, et al: Histological evaluation of chitosan-based biomaterials used for the correction of critical size defects in rat's calvaria. *J Biomed Mater Res A* 2010;93:107-114
- <sup>43</sup>Lahiji A, Sohrabi A, Hungerford DS, et al: Chitosan supports the expression of extracellular matrix proteins in human osteoblasts and chondrocytes. *J Biomed Mater Res* 2000;51:586-595
- <sup>44</sup>Ezoddini-Ardakani F, Azam AN, Yassaei S, et al: Effects of chitosan on dental bone repair. *Health* 2011;3:200-205

- <sup>45</sup>Ezoddini-Ardakani F, Navabazam A, Fatehi F, et al: Histologic evaluation of chitosan as an accelerator of bone regeneration in microdrilled rat tibias. *Dent Res J* 2012;9:694-699
- <sup>46</sup>Muzzarelli R, Biagini G, Pugnali A, et al: Reconstruction of parodontal tissue with chitosan. *Biomaterials* 1989;10:598-603
- <sup>47</sup>Jarcho M: Calcium-phosphate ceramics as hard tissue prosthetics. *Clin Orthop Rel Res* 1981;157:259-278.
- <sup>48</sup>Zhang RY, Ma PX: Poly(alpha-hydroxyl acids) hydroxyapatite porous composites for bone-tissue engineering. I. Preparation and morphology. *J Biomed Mater Res* 1999;44:446-455
- <sup>49</sup>Kong L, Gao Y, Cao W, et al: Preparation and characterization of nano-hydroxyapatite/chitosan composite scaffolds. *J Biomed Mater Res A* 2005;75:275-282
- <sup>50</sup>Zhang Y-F, Cheng X-R, Chen Y, et al: Three-dimensional nanohydroxyapatite/chitosan scaffolds as potential tissue engineered periodontal tissue. *J Biomater Appl* 2007;21:333-349
- <sup>51</sup>Li Z, Ramay HR, Hauch KD, et al: Chitosan-alginate hybrid scaffolds for bone tissue engineering. *Biomaterials* 2005;26:3919-3928
- <sup>52</sup>Zhang Y, Cheng X, Wang J, et al: Novel chitosan/collagen scaffold containing transforming growth factor- $\beta$ 1 DNA for periodontal tissue engineering. *Biochem Biophys Res Commun* 2006;344:362-369
- <sup>53</sup>Gottlow J, Nyman S, Karring T, et al: New attachment formation as the result of controlled tissue regeneration. *J Clin Periodontol* 1984;11:494-503
- <sup>54</sup>Christgau M, Bader N, Felden A, et al: Guided tissue regeneration in intrabony defects using an experimental bioresorbable polydioxanone (PDS) membrane. A 24-month split-mouth study. *J Clin Periodontol* 2002;29:710-723
- <sup>55</sup>Taba M, Jr., Jin Q, Sugai JV, et al: Current concepts in periodontal bioengineering. *Orthod Craniofac Res* 2005;8:292-302
- <sup>56</sup>Czaja WK, Young DJ, Kawecki M, et al: The future prospects of microbial cellulose in biomedical applications. *Biomacromolecules* 2007;8:1-12
- <sup>57</sup>Mendes PN, Rahal SC, Pereira-Junior OC, et al: In vivo and in vitro evaluation of an Acetobacter xylinum synthesized microbial cellulose membrane intended for guided tissue repair. *Acta Vet Scand* 2009;51:1-8
- <sup>58</sup>Wan Y, Huang Y, Yuan C, et al: Biomimetic synthesis of hydroxyapatite/bacterial cellulose nanocomposites for biomedical applications. *Mater Sci Eng C* 2007;27:855-864
- <sup>59</sup>Novaes Jr A, Novaes A, Grisi M, et al: Gengiflex, an alkali-cellulose membrane for GTR: histologic observations. *Braz Dent J* 1993;4:65-71
- <sup>60</sup>Fricain J, Granja P, Barbosa M, et al: Cellulose phosphates as biomaterials. In vivo biocompatibility studies. *Biomaterials* 2002;23:971-980

- <sup>61</sup>Ibara A, Miyaji H, Fugetsu B, et al: Osteoconductivity and biodegradability of collagen scaffold coated with nano- $\beta$ -TCP and fibroblast growth factor 2. *J Nanomater* 2013;2013:46-57
- <sup>62</sup>Soares MP, Soares PV, Pereira AG, et al: Biocompatibility of three bioabsorbable membranes assessed in FGH fibroblasts and human osteoblast like cells culture. *Head Face Med* 2014;10:29
- <sup>63</sup>Postlethwaite AE, Seyer JM, Kang AH: Chemotactic attraction of human fibroblasts to type I, II, and III collagens and collagen-derived peptides. *Proc Natl Acad Sci USA* 1978;75:871-875
- <sup>64</sup>Lucas PA, Caplan AI: Chemotactic response of embryonic limb bud mesenchymal cells and muscle-derived fibroblasts to transforming growth factor-beta. *Connect Tissue Res* 1988;18:1-7
- <sup>65</sup>Caplan AI, Goldberg VM: Principles of tissue engineered regeneration of skeletal tissues. *Clin Orthop Relat Res* 1999;367(Suppl):S12-S16
- <sup>66</sup>Tan W, Krishnaraj R, Desai TA: Evaluation of nanostructured composite collagen-chitosan matrices for tissue engineering. *Tissue Eng* 2001;7:203-210
- <sup>67</sup>Jin QM, Anusaksathien O, Webb SA, et al: Gene therapy of bone morphogenetic protein for periodontal tissue engineering. *J Periodontol* 2003;74:202-213
- <sup>68</sup>Dang JM, Leong KW: Natural polymers for gene delivery and tissue engineering. *Adv Drug Deliv Rev* 2006;58:487-499
- <sup>69</sup>Lynn AK, Yannas IV, Bonfield W: Antigenicity and immunogenicity of collagen. *J Biomed Mater Res B Appl Biomater* 2004;71:343-354
- <sup>70</sup>Bunyaratavej P, Wang HL: Collagen membranes: a review. *J Periodontol* 2001;72:215-229
- <sup>71</sup>Butler WT, Brunn JC, Qin C, et al: Extracellular matrix proteins and the dynamics of dentin formation. *Connect Tissue Res* 2002;43:301-307
- <sup>72</sup>Carter DH, Sloan P: The fibrous architecture of the rat periodontal ligament in cryosections examined by scanning electron microscopy. *Arch Oral Biol* 1994;39:949-953
- <sup>73</sup>Aper T, Schmidt A, Duchrow M, et al: Autologous blood vessels engineered from peripheral blood sample. *Eur J Vasc Endovasc Surg* 2007;33:33-39
- <sup>74</sup>Neidert M, Lee E, Oegema T, et al: Enhanced fibrin remodeling in vitro with TGF- $\beta$ 1, insulin and plasmin for improved tissue-equivalents. *Biomaterials* 2002;23:3717-3731
- <sup>75</sup>Malafaya PB, Silva GA, Reis RL: Natural-origin polymers as carriers and scaffolds for biomolecules and cell delivery in tissue engineering applications. *Adv Drug Deliv Rev* 2007;59:207-233
- <sup>76</sup>Gassling V, Douglas T, Warnke PH, et al: Platelet-rich fibrin membranes as scaffolds for periosteal tissue engineering. *Clin Oral Implants Res* 2010;21:543-549

- <sup>77</sup>Ehrbar M, Metters A, Zammaretti P, et al: Endothelial cell proliferation and progenitor maturation by fibrin-bound VEGF variants with differential susceptibilities to local cellular activity. *J Control Release* 2005;101:93-109
- <sup>78</sup>Schmoekel H, Schense JC, Weber FE, et al: Bone healing in the rat and dog with nonglycosylated BMP-2 demonstrating low solubility in fibrin matrices. *J Orthop Res* 2004;22:376-381
- <sup>79</sup>Flores MG, Yashiro R, Washio K, et al: Periodontal ligament cell sheet promotes periodontal regeneration in athymic rats. *J Clin Periodontol* 2008;35:1066-1072
- <sup>80</sup>Isogai N, Landis WJ, Mori R, et al: Experimental use of fibrin glue to induce site-directed osteogenesis from cultured periosteal cells. *Plast Reconstr Surg* 2000;105:953-963
- <sup>81</sup>Bensaid W, Triffitt JT, Blanchat C, et al: A biodegradable fibrin scaffold for mesenchymal stem cell transplantation. *Biomaterials* 2003;24:2497-2502
- <sup>82</sup>Yoshida T, Washio K, Iwata T, et al: Current status and future development of cell transplantation therapy for periodontal tissue regeneration. *Int J Dent* 2012;2012:307024
- <sup>83</sup>Choukroun J, Diss A, Simonpieri A, et al: Platelet-rich fibrin (PRF): a second-generation platelet concentrate. Part IV: clinical effects on tissue healing. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 2006;101:e56-e60
- <sup>84</sup>Catelas I, Sese N, Wu BM, et al: Human mesenchymal stem cell proliferation and osteogenic differentiation in fibrin gels in vitro. *Tissue Eng* 2006;12:2385-2396
- <sup>85</sup>Bensaid W, Triffitt J, Blanchat C, et al: A biodegradable fibrin scaffold for mesenchymal stem cell transplantation. *Biomaterials* 2003;24:2497-2502
- <sup>86</sup>Yoshida T, Washio K, Iwata T, et al: Current status and future development of cell transplantation therapy for periodontal tissue regeneration. *Int J Dent* 2012;2012:307024
- <sup>87</sup>Chen F-M, Sun H-H, Lu H, et al: Stem cell-delivery therapeutics for periodontal tissue regeneration. *Biomaterials* 2012;33:6320-6344
- <sup>88</sup>Chen F-M, Jin Y: Periodontal tissue engineering and regeneration: current approaches and expanding opportunities. *Tissue Eng Part B Rev* 2010;16:219-255
- <sup>89</sup>Catón J, Bostanci N, Remboutsika E, et al: Future dentistry: cell therapy meets tooth and periodontal repair and regeneration. *J Cell Mol Med* 2011;15:1054-1065
- <sup>90</sup>Lin NH, Gronthos S, Bartold PM: Stem cells and future periodontal regeneration. *Periodontology* 2000 2009;51:239-251

- <sup>91</sup>Hasegawa N, Kawaguchi H, Hirachi A, et al: Behavior of transplanted bone marrow-derived mesenchymal stem cells in periodontal defects. *J Periodontol* 2006;77:1003-1007
- <sup>92</sup>Kawaguchi H, Hayashi H, Mizuno N, et al: Cell transplantation for periodontal diseases. A novel periodontal tissue regenerative therapy using bone marrow mesenchymal stem cells. *Clin Calcium* 2005;15:99-104
- <sup>93</sup>Weng Y, Wang M, Liu W, et al: Repair of experimental alveolar bone defects by tissue-engineered bone. *Tissue Eng* 2006;12:1503-1513
- <sup>94</sup>Li H, Yan F, Lei L, et al: Application of autologous cryopreserved bone marrow mesenchymal stem cells for periodontal regeneration in dogs. *Cells Tissues Organs* 2009;190:94-101
- <sup>95</sup>Seo B-M, Miura M, Gronthos S, et al: Investigation of multipotent postnatal stem cells from human periodontal ligament. *Lancet* 2004;364:149-155
- <sup>96</sup>Bartold PM, Shi S, Gronthos S: Stem cells and periodontal regeneration. *Periodontology* 2000 2006;40:164-172
- <sup>97</sup>Shin S-Y, Park H-N, Kim K-H, et al: Biological evaluation of chitosan nanofiber membrane for guided bone regeneration. *J Periodontol* 2005;76:1778-1784
- <sup>98</sup>Lee YM, Park YJ, Lee SJ, et al: Tissue engineered bone formation using chitosan/tricalcium phosphate sponges. *J Periodontol* 2000;71:410-417
- <sup>99</sup>Zhang YZ, Venugopal JR, El-Turki A, et al: Electrospun biomimetic nanocomposite nanofibers of hydroxyapatite/chitosan for bone tissue engineering. *Biomaterials* 2008;29:4314-4322
- <sup>100</sup>Bumgardner JD, Wiser R, Gerard PD, et al: Chitosan: potential use as a bioactive coating for orthopaedic and craniofacial/dental implants. *J Biomat Sci-Polym E* 2003;14:423-438
- <sup>101</sup>Taba M, Jin Q, Sugai J, et al: Current concepts in periodontal bioengineering. *Orthod Craniofac Res* 2005;8:292-302
- <sup>102</sup>Gutowska A, Jeong B, Jasionowski M: Injectable gels for tissue engineering. *Anat Rec* 2001;263:342-349
- <sup>103</sup>Glowacki J, Mizuno S: Collagen scaffolds for tissue engineering. *Biopolymers* 2008;89:338-344
- <sup>104</sup>Wallace DG, Rosenblatt J: Collagen gel systems for sustained delivery and tissue engineering. *Adv Drug Deliv Rev* 2003;55:1631-1649
- <sup>105</sup>Ahmed TA, Dare EV, Hincke M: Fibrin: a versatile scaffold for tissue engineering applications. *Tissue Eng Part B Rev* 2008;14:199-215
- <sup>106</sup>Osathanon T, Linnes ML, Rajachar RM, et al: Microporous nanofibrous fibrin-based scaffolds for bone tissue engineering. *Biomaterials* 2008;29:4091-4099

- <sup>107</sup>Boateng JS, Matthews KH, Stevens HN, et al: Wound healing dressings and drug delivery systems: a review. *J Pharm Sci* 2008;97:2892-2923
- <sup>108</sup>Ji QX, Zhong de Y, Lu R, et al: In vitro evaluation of the biomedical properties of chitosan and quaternized chitosan for dental applications. *Carbohydr Res* 2009;344:1297-1302
- <sup>109</sup>Czaja W, Krystynowicz A, Bielecki S, et al: Microbial cellulose—the natural power to heal wounds. *Biomaterials* 2006;27:145-151
- <sup>110</sup>Moioli EK, Clark PA, Xin X, et al: Matrices and scaffolds for drug delivery in dental, oral and craniofacial tissue engineering. *Adv Drug Deliv Rev* 2007;59:308-324
- <sup>111</sup>Ferreira AM, Gentile P, Chiono V, et al: Collagen for bone tissue regeneration. *Acta Biomater* 2012;8:3191-3200.
- <sup>112</sup>Bora A, Zahir S, Kundu GK, et al: Regenerative pulp therapy for immature nonvital teeth with plasma-rich fibrin. *SRM J Res Dent Sci* 2015;6:198-202
- <sup>113</sup>Trindade R, Albrektsson T, Wennerberg A: Current concepts for the biological basis of dental implants: foreign body equilibrium and osseointegration dynamics. *Oral Maxillofac Surg Clin North Am* 2015;27:175-183
- <sup>114</sup>Patel J, Patel S, Kadam C: Choukroun's platelet rich fibrin in regenerative dentistry. *Univ Res J Dent* 2013;3:22-25
- <sup>115</sup>Croisier F, Jérôme C: Chitosan-based biomaterials for tissue engineering. *Eur Polym J* 2013;49:780-792
- <sup>116</sup>Sharma S, Srivastava D, Grover S, et al: Biomaterials in tooth tissue engineering: a review. *J Clin Diagn Res* 2014;8:309-315
- <sup>117</sup>Kim IY, Seo SJ, Moon HS, et al: Chitosan and its derivatives for tissue engineering applications. *Biotechnol Adv* 2008;26:1-21
- <sup>118</sup>Akncbay H, Senel S, Ay ZY: Application of chitosan gel in the treatment of chronic periodontitis. *J Biomed Mater Res B Appl Biomater* 2007;80:290-296
- <sup>119</sup>Mendes PN, Rahal SC, Pereira-Junior OC, et al: In vivo and in vitro evaluation of an *Acetobacter xylinum* synthesized microbial cellulose membrane intended for guided tissue repair. *Acta Vet Scand.* 2009;51:12
- <sup>120</sup>Petersen JK, Krogsgaard J, Nielsen KM, et al: A comparison between 2 absorbable hemostatic agents—gelatin sponge (Spongostan) and oxidized regenerated cellulose (Surgicel). *Int J Oral Surg* 1984;13:406-410
- <sup>121</sup>Bunyaratavej P, Wang HL: Collagen membranes: a review. *J Periodontol* 2001;72:215-229.
- <sup>122</sup>d'Aquino R, De Rosa A, Lanza V, et al: Human mandible bone defect repair by the grafting of dental pulp stem/progenitor cells and collagen sponge biocomplexes. *Eur Cells Mater* 2009;18:75-83

**NOT THE PUBLISHED VERSION; this is the author's final, peer-reviewed manuscript.** The published version may be accessed by following the link in the citation at the bottom of the page.

Mina D. Fahmy and Mehdi Razavi contributed equally to this work.

The authors deny any conflict of interest.